

Classification	Insulating Brick ASTM C 155-88, Group No. 16		
Physical Properties	Max. Service Temperature	°C	850
	Bulk Density	kg/m ³	640
	Apparent Porosity	%	62
	Cold Crushing Strength	kg/cm ²	15
	Modulus of Rupture	kg/cm ²	6
	Permanent Linear Change After Heating at 845 °C	%	-0.30
	Chemical Composition	Alumina (Al ₂ O ₃)	%
Silica (SiO ₂)		%	49.5
Lime (CaO)		%	27.5
Iron Oxide (Fe ₂ O ₃)		%	0.5
Thermal Expansion	400 °C	%	0.19
	800 °C	%	0.24
Thermal Conductivity	350 °C	W/m.K	0.13
	400 °C	W/m.K	0.13
	600 °C	W/m.K	0.14
	800 °C	W/m.K	0.15

The above data are typical properties of 9" commercial straight brick. The data are subjected to reasonable variations and should not be used for specification purposes.

ASTM test methods, and SRIC's written procedure, where applicable, used for determination of data.

THE SIAM REFRACTORY INDUSTRY CO., LTD.

1 Siam Cement Road, Bangsue, Bangkok 10800 Thailand Tel. (+66 2) 586-3242-53 Fax. (+66 2) 586-2982, 587-2149

